



Oxford Performance Materials

30 South Satellite Road • South Windsor, CT 06074 USA • T: +1.860.698.9300 • F: +1.860.698.9978 • [www.oxfordpm.com](http://www.oxfordpm.com)

## High Performance Thermoplastic OXPEKK® Materials Unfilled and Reinforced Industrial Grades

PROPERTY	TEST METHOD	OXPEKK-SP	OXPEKK-C	OXPEKK-CE	OXPEKK-SP30G	OXPEKK-C30G	OXPEKK-C40G	OXPEKK-C30C	OXPEKK-C40C	OXPEKK-BG
		Amorphous	Crystalline Injection	Crystalline Extrusion	Superior Process	Crystalline	Crystalline	Crystalline	Crystalline	Bearing Grade
		Unfilled	Unfilled	Unfilled	30% Glass	30% Glass	40% Glass	30% Carbon Fiber	40% Carbon Fiber	
Color		Amber	Beige	Beige	Amber	Beige	Beige	Black	Black	Black
Linear Mold Shrinkage, in/in	ASTM D955	<0.005	0.014	0.014	0.002	0.003	0.002	0.001	0.0005	0.002
Specific Gravity, g/cm³	ASTM D792	1.28	1.31	1.31	1.50	1.51	1.62	1.36	1.45	1.46
Water Absorption @ 24hr, %	ASTM D570	<0.20	<0.20	<0.20	0.10	<0.03	<0.03	<0.03	<0.03	<0.04
<b>MECHANICAL</b>										
Tensile Strength (Break), Kpsi	ASTM D638	13	16	16	26	27	29	36	47	25
Tensile Modulus, Mpsi	ASTM D638	0.5	0.64	0.64	1.6	1.8	2.9	4	7	1.8
Elongation (Break), %	ASTM D638	80	12	60	2.3	1.8	1.6	1.2	1.3	2
Flexural Strength @ 5% strain, Kpsi	ASTM D790	20	28	28	--	--	--	--	--	--
Flexural Strength, Kpsi	ASTM D790	--	--	--	35	37	42	56	65	36
Flexural Modulus, Mpsi	ASTM D790	0.49	0.66	0.66	1.6	1.6	2.1	3.5	4.5	1.8
Izod, Notched, ft-lb/in	ASTM D256	0.9	1	1.2	2	1.8	1.6	1.05	1.8	1.2
Compressive Strength, Kpsi	ASTM D695	15	30	30	--	32	--	--	--	32
Coefficient of Friction, Static	ASTM D1894	0.285	0.262	0.262	--	--	--	0.22	0.22	0.25
Hardness, Rockwell M	ASTM D785	86	88	88	--	103	--	--	--	90
<b>THERMAL</b>										
Tm-Melting Point, oF (°C)	DSC	577 (303)	680 (360)	680 (360)	577 (303)	680 (360)	680 (360)	680 (360)	680 (360)	680 (360)
Tg-Glass Transition, oF (°C)	DSC	310 (155)	325 (163)	325 (163)	310 (155)	325 (163)	325 (163)	325 (163)	325 (163)	325 (163)
Melt Flow, g/10min	ASTM D1638	35-45 (380C/8.4kg)	100-120 (400C/8.4kg)	20-30 (400C/8.4kg)	--	--	--	14-18 (400C/8.4kg)	10-12 (400C/8.4kg)	--
Flammability Rating	UL94	V-0	V-0	V-0	V-0	V-0	V-0	V-0	V-0	V-0
HDT @ 264 psi, oF (°C)	ASTM D648	286 (141)	347 (175)	347 (175)	--	610 (321)	619 (326)	610 (321)	621 (327)	>572 (300)
Thermal Conductivity, BTU-in/Hr-Ft²°F	ASTM C177	1.75	1.75	1.75	--	--	--	--	--	1.75
CTE (<Tg), 10-6/°F	ASTM D696	42.8	11.7	11.7	--	8.9	6.5	5.6	6	25
<b>ELECTRICAL</b>										
Dielectric Strength, V/mil	ASTM D149	600	600	600	--	--	--	--	--	--
Dielectric Constant @ 1KHz	ASTM D150	3.3	3.3	3.3	--	--	--	--	--	--
Volume Resistivity, ohm-cm	ASTM D257	1.0E+16	1.0E+16	1.0E+16	--	--	--	--	--	--
Surface Resistivity, ohm	ASTM D257	2.0E+16	2.0E+16	2.0E+16	--	--	--	--	--	--
Dissipation Factor @ 1KHz	ASTM D150	4.0E-03	4.0E-03	4.0E-03	--	--	--	--	--	--

NOTICE TO USERS: To the best of our knowledge, the information contained in this publication is accurate, however we do not assume any liability whatsoever for the accuracy and completeness of such information. The analysis techniques included in this publication are often simplifications and, therefore, approximate in nature. Any determination of the suitability of a particular material for any use contemplated by the user is the sole responsibility of the user. Material data and values included in this publication are either based on testing of laboratory test specimens and represent data or were extracted from various published sources. All are believed to be representative. These values are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication.