



Oxford Performance Materials

30 South Satellite Road • South Windsor, CT 06074 USA • T: +1.860.698.9300 • F: +1.860.698.9978 • www.oxfordpmp.com

High Performance Thermoplastic OXPEKK® Materials Medical Grades (MG) and Implant Grades (IG) – Unfilled

MEDICAL GRADE			OXPEKK-MG100		OXPEKK-MG200		OXPEKK-MG300	
IMPLANT GRADE			OXPEKK-IG100		OXPEKK-IG200		OXPEKK-IG300	
PROPERTIES	English Unit	Metric Unit	Amorphous Grade		Crystalline Injection Grade		Crystalline Extrusion Grade	
Form			Pellets		Pellets		Extruded Shapes	
Specific Gravity	lb/cb-ft	g/cm^3	79.9	1.28	81.8	1.31	81.8	1.31
Linear Mold Shrinkage	in/in	%	<0.005	<0.5	0.014	1.4	0.014	1.4
Water Absorption @ 24 hrs	%	%	<0.2	<0.2	<0.20	<0.20	<0.20	<0.20
MECHANICAL								
Tensile Strength (Break)	Kpsi	MPa	13	89.6	16	110.3	16	110.3
Tensile Strength (Yield)	Kpsi	MPa	15	103	20	138	20	138
Tensile Modulus	Mpsi	GPa	0.5	3.45	0.55	3.8	0.64	4.41
Elongation (Break)	%	%	80+	80+	12	12	30+	30+
Elongation (Yield)	%	%	6	6	4	4	4.5	4.5
Flexural Strength @ 5% strain	Kpsi	MPa	20	137.9	28	193.1	28	193.1
Flexural Modulus	Mpsi	GPa	0.49	3.38	0.66	4.55	0.66	4.55
Izod, Notched	ft-lbf/in	J/m	0.9	48.0	1	53.4	1.2	64.1
Compressive Strength	Kpsi	MPa	15	103.4	30	206.8	30	206.8
Shear Strength	Kpsi	MPa	---	---	20	137.9	---	---
Hardness, Rockwell	M	M	86	86	88	88	88	88
THERMAL								
Melting Point	°F	°C	585	307	680	360	680	360
Glass Transition	°F	°C	310	155	325	163	325	163
Melt Index ⁽¹⁾	g/10min	g/10min	35-45	35-45	100-120	100-120	20-30	20-30
HDT @264 psi (1.8 MPa)	°F	°C	286	141	347	175	347	175
CTE (<T _g)	10 ⁻⁶ /°F	10 ⁻⁶ /°C	42.8	77.0	11.7	21.1	11.7	21.1
<i>All numbers represent typical values</i>								
⁽¹⁾ Test Conditions: 380°C/8.4kg for OXPEKK-MG100 and 400°C/8.4kg for OXPEKK-MG/IG200 & OXPEKK-MG/IG300								

NOTICE TO USERS: To the best of our knowledge, the information contained in this publication is accurate, however we do not assume any liability whatsoever for the accuracy and completeness of such information. The analysis techniques included in this publication are often simplifications and, therefore, approximate in nature. Any determination of the suitability of a particular material for any use contemplated by the user is the sole responsibility of the user. Material data and values included in this publication are either based on testing of laboratory test specimens and represent data or were extracted from various published sources. All are believed to be representative. These values are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication.